## **EXHIBIT A**

Attorney Docket No.: 19461-0005US1 / 548062

## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant: Kimihiro Mabuchi et al. Art Unit: 1797

Serial No.: 10/599,128 Examiner: Krishnan S. Menon

Filed : September 20, 2006 Conf. No. : 4588

Title : SEPARATION MEMBRANE WITH SELECTIVE PERMEABILITY AND

PROCESS FOR PRODUCING THE SAME

Commissioner for Patents P.O. Box 1450 Alexandria, VA 22313-1450

## **DECLARATION OF MR. KIMIHIRO MABUCHI UNDER 37 C.F.R. § 1.132**

- I, Kimihiro Mabuchi, hereby declare:
- 1. I am a co-inventor of the subject matter of the above-captioned application, which relates to separation membranes with selective permeability. At the time the subject invention was made, I served as an institute member in Membrane Research and Development Center of Toyo Boseki Kabushiki Kaisha, Osaka, Japan. I had about nine years' experience in the relevant field at the time the invention was made. I am currently employed by Toyo Boseki Kabushiki Kaisha.
- 2. I have been advised and understand that claims 1-8, 10, and 12-15 in the above-referenced application are rejected as being obvious over Shimagaki, U.S. Patent No. 6,103,117 ("Shimagaki") in the office action issued on January 5, 2010. Claim 1, the only independent claim, recites a separation membrane having at least the following features:
  - (a) a ratio [D]/[C] between the polyvinyl pyrrolidone content [D] in the uppermost layer of a surface on non-blood contacting side and the polyvinyl pyrrolidone content [C] in the uppermost layer of a surface on blood contacting side is 1.1 or higher; and
  - (b) when bovine blood at a temperature of 37°C having hematocrit value of 30% and containing 6 to 7 g/dl of total proteins and sodium citrate is flowed through a module containing the separation membrane at a flow rate of 200 ml/min. and a filtration rate of 20 ml/min.:
  - (i) a sieving coefficient of albumin [A] becomes not less than 0.01 and not more than 0.1 after 15 minutes; and
  - (ii) a sieving coefficient of albumin [B] becomes not less than 0.005 and less than 0.04 after 2 hours.

Applicant: Kimihiro Mabuchi et al. Attorney's Docket No.: 19461-0005US1 / 548062

Serial No.: 10/599,128

Filed: September 20, 2006

Page : 2 of 4

3. To compare the membranes described in Shimagaki and the membranes claimed in the present application, I prepared four separation membranes following the procedures described in Examples 4-7 in Shimagaki, which are believed to be the closest examples to the membrane recited in claim 1.

4. Specifically, as shown in Table 1 below, the membranes prepared by Examples 4-7 in Shimagaki have an albumin sieving coefficient between 0.005 and 0.04 after flowing blood through them for 1 hour and <u>might</u> satisfy feature (b)(ii) recited in claim 1 (which requires an albumin sieving coefficient between not less than 0.005 and less than 0.04 after flowing blood through a membrane for 2 hours). On the other hand, the membranes prepared by the Examples in Shimagaki other than Examples 4-7 have an albumin sieving coefficient less than 0.005 after flowing blood through them for 1 hour and, therefore, cannot satisfy feature (b)(ii) recited in claim 1.

Table 1

|        | Albumin                 | Albumin Sieving | Notes  |
|--------|-------------------------|-----------------|--|
|        | Permeability            | Coefficient     |  |
|        | (%)                     |                 |  |
| Ex. 1  | 0.12                    | 0.0012          | Out of the range in feature (b)(ii)          |
| Ex. 2  | 0.17                    | 0.0017          | Out of the range in feature (b)(ii)          |
| Ex. 3  | 0.32                    | 0.0032          | Out of the range in feature (b)(ii)          |
| CEx. 1 | 0.12                    | 0.0012          | Out of the range in feature (b)(ii)          |
| Ex. 4  | 0.75                    | 0.0075          | Might be within the range in feature (b)(ii) |
| Ex. 5  | 0.58                    | 0.0058          | Might be within the range in feature (b)(ii) |
| Ex. 6  | 1.38                    | 0.0138          | Might be within the range in feature (b)(ii) |
| CEx. 2 | 0.12                    | 0.0012          | Out of the range in feature (b)(ii)          |
| Ex. 7  | 1.2                     | 0.0120          | Might be within the range in feature (b)(ii) |
| Ex. 8  | 0.4                     | 0.0040          | Out of the range in feature (b)(ii)          |
| Ex. 9  | 0.1                     | 0.0010          | Out of the range in feature (b)(ii)          |
|        | $0.2 (1.0 \text{ m}^2)$ | 0.0020          | Out of the range in feature (b)(ii)          |
| Ex. 11 | $0.1 (1.6 \text{ m}^2)$ | 0.0010          | Out of the range in feature (b)(ii)          |
|        | $0.2 (1.8 \text{ m}^2)$ | 0.0020          | Out of the range in feature (b)(ii)          |
| CEx. 3 | 0.2                     | 0.0020          | Out of the range in feature (b)(ii)          |
| CEx. 4 | 0.3                     | 0.0030          | Out of the range in feature (b)(ii)          |

<sup>&</sup>lt;sup>1</sup> A membrane having an albumin sieving coefficient less than 0.005 after flowing blood through the membrane for 1 hour would also have an albumin sieving coefficient less than 0.005 after flowing blood through the membrane for 2 hours

-

Applicant: Kimihiro Mabuchi et al. Attorney's Docket No.: 19461-0005US1 / 548062

Serial No.: 10/599,128

Filed: September 20, 2006

Page : 3 of 4

5. The conditions for preparing the membranes in Examples 4-7 described in Shimagaki and the properties of the membranes thus obtained are summarized in Table 2 below. For comparison, Table 2 also includes the conditions for preparing a membrane claimed in the present application and its corresponding properties.

Table 2

|                          |  | Preferred/Claimed range for Invention  | Example 4<br>(US8103117)                                  | Example 5 (US6103117) | Example 6 (U\$6103117) | Example 7<br>(US5103117) |
|--------------------------|--|--|---|-----------------------|------------------------|--------------------------|
|                          | Polysulfon   | -                                      | 18  | 19                    | -                      | 18                       |
| Film-forming Solution    |  | M: 10.000 to 1.500.000                 | K30   | <b>-</b>              | K60                    | K30+K90                  |
|                          | PVP, parts   | ************************************** | 9   | -                     | -                      | 8+3                      |
|                          | DMAc, parts  |  | 71.7  | 70.7                  | 70,0                   | 71.95                    |
|                          | Water, parts   |  | 1.3   | 1.3                   | 2.0                    | 1.05                     |
|                          | PVP/Polysulfon<br>(mass %)                               | 10~18                                  | 50.0  | 47.4                  | 474                    | 50.0                     |
|                          |  | Nitrogen atmosphere                    | Air almosphere Air atmosphere Air atmosphere Air atmosphe |                       |                        |                          |
|                          | Dissolution condition                                    | 70dez or lower.<br>within 3 hours.     | 90deg + 12hrs   |                       | -                      | 80deg # 12hrs            |
|                          | DMAc/Water   | 30~60/70~40                            | 70/30   | -                     | 63/37                  | 60/40                    |
| Inner Solution           | Temperature (deg)  | 0~40                                   | Not controled   | -                     | •                      | _                        |
| paler Cultadet           | (Temp. of Film-forming soln.)<br>—(Temp. of Inner soln.) | 30~60                                  | Not controled   |                       | 4                      | -                        |
| Nozzle                   | Extrusion width of Film-<br>forming Soln.                | 100 μ m or lower                       | 50µm<br>(0.3-0.2)mm                                       | -                     | -                      | -                        |
|                          | Temperature (deg)  | 20~90                                  | -   | ****                  | *****                  | 30                       |
|                          | Length(mm)   |  | 250   | •                     | 350                    | 250                      |
| Dry Zone                 | Humidity(%)  |  | 85  | <b>\$</b>             | -                      | 68                       |
|                          | Composition  |  | ***   |                       | -                      | DMAc/Water               |
| Guagulation Bath         | Composition ratio  |  | -   |                       |                        | 20/80                    |
|                          | Temperature (deg)  |  | 50  | -                     | -                      | 40                       |
| Glycerine Bath           | (8)  | -                                      | -   | -                     | _                      | 58                       |
| Drying                   | Temperature (deg)  | 20-80                                  | 65  | 65                    | 65                     | 65                       |
| Spinning Speed           | (m/min)  |  | *   |                       |                        | 40                       |
| Washing with pure water  |  | Applied                                |   | <b>-</b>              |                        | 80deg.+30min             |
| Inner Diameter           | (µm)   |  |   | -                     |                        | 200                      |
| Outer Diameter           | (µm)   |  |   | <b>6</b>              | -                      | 280                      |
| hickness of hollow Fiber | (µm)   | 25-45                                  | -   | ***                   | -                      | 40                       |
| (C)                      | (mass %)   | 20-40                                  | 35  | 33                    | 40                     | 45                       |
| [D]                      | (mass %)   | 25-50                                  | 35  | 31                    | 37                     | 43                       |
| [D]/[C]                  |  | 1.1 or higher                          | 1.0   | 0.9                   | 0.9                    | 1.0                      |
| [A]                      |  | 0.01-0.1                               | 0.048   | 0.035                 | 0.031                  | 0.038                    |
| [8]                      |  | 0.005-0.04                             | 0.006   | 0.003                 | 0.012                  | 0.013                    |

Parameters according to the invention

[A]: Sieving coefficient of albumin after 15 minutes

[B]. Sieving coefficient of albumin after 2 hours
[C]: Polyvinyl pyrrolidone content in the uppermost layer of a surface on blood contacting side

[D]: Polyvinyl pyrrolidone content in the uppermost layer of a surface on non-blood contacting side

Note

\*1. Condition not clearly described in USP \*2: Condition not clearly described in USP

Applicant: Kimihiro Mabuchi et al.

Serial No.: 10/599,128

Filed : September 20, 2006

Page : 4 of 4

6. As shown in Table 2, even though the membranes prepared by Examples 4-7 in Shimagaki may have an albumin sieving coefficient that falls within the range in feature (b)(ii) recited in claim 1, they do not possess a [D]/[C] ratio of 1.1 or higher, as recited in feature (a) of claim 1. Specifically, Table 2 shows that the membranes prepared by Examples 4-7 in Shimagaki have a [D]/[C] ratio ranging from 0.9-1.0, which is less than the [D]/[C] ratio of 1.1 or higher recited in feature (a) of claim 1.

7. I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

roly /st. 20/0

Date:

Respectfully submitted,

Kimihiro Mabuchi

Toyo Boseki Kabushiki Kaisha 1-1, Katata 2-Chome, Ohtsu-shi

Attorney's Docket No.: 19461-0005US1 / 548062

Shiga, Japan

30545388.doc